



PRODUCT DATA

CHANDROL TYRE WAXES

PRODUCT CATEGORY: CHANDROL MICRO WAXES

PRODUCT NAME: CHANDROL MCW TYRE - 1080

Description

Products made from Natural or Synthetic rubbers are exposed to natural sunlight when used Chandrol micro wax helps create a thin film of wax reducing the damage caused to the product by harmful UV rays and ozone penetration. CHANDROL MCW TYRE - 1080 is specifically designed for tyre applications both made from synthetic and natural rubbers, CHANDROL MCW TYRE – 1080 is designed keeping in minds the hot weather of India and the Indian road conditions and operating conditions of tyre in India.

The high centrifugal force obtained when tyre is being used combined with high temperatures will results in wax coming on the surface of the tyre and forming a thin film protecting the tyre from damage from ozone and UV rays thus protecting the tyres from any damage.

Application

Protecting the tyres from harmful UV rays and Ozone exposure when the tyre is in use and the operating temperature is high specifically designed for Indian roads and weather conditions

Benefits

Easy dispersion

Even and timely migration

UV protection

Ozone protection

Factory Address : E-14, M.I.D.C., Tarapur, Boisar, Thane - 401506, Maharashtra

Registered Address : 4th Floor, Hafizain Bldg, 129/131, Kazi Sayed Street, Masjid (W), Mumbai - 400 003



DATE: 09/07/2016

CERTIFICATE OF ANALYSIS
CHANDROL MCW TYRE - 1080

Sr. No.	Parameter	Specification	Chandrol MCW Tyre-1080	Test Method
1	Appearance	White to Yellow Pallets	Off White Pellets	Visual
2	Congealing Point	63.0°C – 70°C	67.0°C	ASTM D 938
3	Drop Melting Point	75.0°C- 82.0°C	78.0°C	ATSM D 127
4	Viscosity @ 100°C	6.5 – 7.2 Cst	6.8 Cst	ASTM D 445
5	Refractive Index @ 100°C	1.4288 ± 0.0032	1.430	ASTM D 1747
6	Ash Content	0.1 % Max	0.019 %	ASTM D 482
7	Oil Content	1.0% Max	0.79%	ASTM D 721
8	Centring Point of the Peak	C ₂₅ ± 1 C ₃₂ ± 1	C ₂₆ C ₃₂	ASTM D 5442
9	Normal Hydro Carbon			ASTM D 5442
	C ₂₀ =	0.1 – 1.2%	0.97%	
	C ₂₁ =	0.8 – 3.0%	2.60%	
	C ₂₂ =	1.5 – 5.0%	4.47%	
	C ₂₃ =	3.8 – 6.5%	5.84%	
	C ₂₄ =	5.5 – 8.5%	6.56%	
	C ₂₅ =	6.0 – 9.0%	7.04%	
	C ₂₆ =	6.0 – 9.0%	7.16%	
	C ₂₇ =	5.5 – 8.5%	7.05%	
	C ₂₈ =	5.8 – 8.0%	6.29%	
	C ₂₉ =	6.0 – 8.5%	5.64%	
	C ₃₀ =	6.0 – 8.5%	5.50%	
	C ₃₁ =	5.5 – 8.5%	6.07%	
	C ₃₂ =	5.5 – 8.5%	6.25%	
	C ₃₃ =	5.5 – 7.5%	6.15%	
	C ₃₄ =	4.0 – 7.0%	5.20%	
	C ₃₅ =	3.0 – 6.0%	4.18%	

Factory Address : E-14, M.I.D.C., Tarapur, Boisar, Thane - 401506, Maharashtra

Registered Address : 4th Floor, Hafizain Bldg, 129/131, Kazi Sayed Street, Masjid (W), Mumbai - 400 003

	C ₃₆ =	1.0 – 5.0%	2.80%	
	C ₃₇ =	0.8 – 4.0%	1.93%	
	C ₃₈ =	0.5 – 3.5%	0.63%	
	C ₃₉ =	0.0 – 2.0%	0.20%	
	C ₄₀ =	0.0 – 1.2%	0.07%	
10	Normal Hydro Carbon			ASTM D 5442
	C ₂₀ - C ₂₄	11.0 – 23.0%	20.44%	
	C ₂₅ - C ₂₉	28.0 – 44.0%	33.17%	
	C ₃₀ - C ₃₄	25.0 – 50.0%	29.17%	
	C ₃₅ - C ₄₀	4.0 – 20.0%	9.80%	

Prepared By:

Approved By:

Factory Address : E-14, M.I.D.C., Tarapur, Boisar, Thane - 401506, Maharashtra

Registered Address : 4th Floor, Hafizain Bldg, 129/131, Kazi Sayed Street, Masjid (W), Mumbai - 400 003