



**Chandri Paper & Allied Products Pvt. Ltd.**

**TEST REPORT**

Customer Name:	
Invoice No. :	Invoice Date :
Batch No. :	Test Report Date: 17/05/16
Grade : Chandrol Microfin 63	Quantity :
Product Code :	Vehicle No. :

Sr. No.	PARAMETERS	METHOD	MIN.	MAX.	RESULT
1	Appearance	Visual	Light Yellow		Light Yellow
2	Colour on Melting	ASTM D 1500	Report	-	1.0
3	Melting Point, °C	ASTM D 87	Report	-	62.5
4	Congealing Point, °C	ASTM D 938	Report	-	56
5	Flash Point (COC), °C	ASTM D 92	Report	-	245
6	Needle Penetration @ 30°C of Slab	ASTM D 1321	Report	-	50

Remark: OK

Remark:

Approved By:

Factory Address: E - 14, M.I.D.C., Tarapur, Boisar, Thane - 401506, Maharashtra  
Registered Address: 4<sup>th</sup> Floor, Hafizian Bldg., Kazi Sayed Street, Masjid (W), Mumbai - 400 003



**Chandri Paper & Allied Products Pvt. Ltd.**

**TEST REPORT**

Customer Name:	
Invoice No. :	Invoice Date :
Batch No. : L-205	Test Report Date: 17/05/16
Grade : MC Wax	Quantity :
Product Code :	Vehicle No. :

Sr. No.	PARAMETERS	METHOD	MIN.	MAX.	RESULT
1	Appearance	Visual	White Solid Wax		White Flakes
2	Colour on Melting	ASTM D 1500	Report	-	1.0
3	Melting Point, °C	ASTM D 87	Report	-	71
4	Congealing Point, °C	ASTM D 938	Report	-	65
5	Flash Point (COC), °C	ASTM D 92	Report	-	230
6	Needle Penetration @ 30°C of Slab	ASTM D 1321	Report	-	55

Remark: OK

Remark:

Approved By:

Factory Address: E - 14, M.I.D.C., Tarapur, Boisar, Thane - 401506, Maharashtra  
Registered Address: 4<sup>th</sup> Floor, Hafizian Bldg., Kazi Sayed Street, Masjid (W), Mumbai - 400 003



**Chandri Paper & Allied Products Pvt. Ltd.**

**TEST REPORT**

Customer Name:	
Invoice No. :	Invoice Date :
Batch No. :	Test Report Date: 17/05/16
Grade : CB650	Quantity :
Product Code :	Vehicle No. :

Sr. No.	PARAMETERS	METHOD	MIN.	MAX.	RESULT
1	Appearance	Visual	Light Yellow Flakes Wax		Light Yellow Flakes Wax
2	Colour on Melting	ASTM D 1500	-	1.5	0.5
3	Melting Point, °C	ASTM D 87	60	-	71
4	Congealing Point, °C	ASTM D 938	50	-	61.5
5	Flash Point (COC), °C	ASTM D 92	200	-	233
6	Needle Penetration @ 25°C of Slab	ASTM D 1321	20	60	29
7	Oil Content, % wt.	ASTM D 721-06	1.5	2.0	1.59
8	Packing	30 kg in box			

Remark: OK  
Remark:

Approved By:

Factory Address: E - 14, M.I.D.C., Tarapur, Boisar, Thane - 401506, Maharashtra  
Registered Address: 4<sup>th</sup> Floor, Hafizian Bldg., Kazi Sayed Street, Masjid (W), Mumbai - 400 003